

Plant: HDPE

Grade/Product Name: HF4760 (BL3)

Grade: Blow Molding

Test/Composition	value	Unit	Method
Density	0.954±0.002	g/cm ³	ISO 1183
FRR 21.6/5	1943		
MFR 190°/21.6	2384	g/10min	ISO1133
MFR190°/5	1.2±0/3	g/10min	ISO1133
Notched Impact (23°C)	29	kJ/mm ²	ISO179/1eA

Main Application: Small blow molding

Notes: - Test specimen from compression molded sheet at 23°C

- FRR values are statistical and calculated by dividing MFR values.
- Notch Impact Test specimen from compressed molded sheet 23°C and The data quoted are average

values.

