

LL6910KJ

Product Technical Information

LLDPE film products

Applications

LL6910AA is particularly suitable for use in lean and rich blend blown film applications, such as overwrap, counter bags, shrink film (lean blends, 10 to 30% LLDPE) and boil-in-the-bag applications.

Benefits and Features

LL6910KJ is a linear low density polyethylene copolymer containing hexene-1 as the co-monomer. It offers the following properties:

- Very high stiffness and downgauging potential
- Good optical properties
- High temperature resistance
- High water vapour barrier properties
- High creep resistance
- Excellent sealability and hot-tack strength

LL6910KJ gives high slip film with easy opening properties when used pure in the thickness range 30 - 70 μm . Addition of other polymers, masterbatches and pigments, or use of other thicknesses may alter film slip and antiblock performance.

If corona treatment is necessary, the level should normally be in the range 38-48 mN/m.

We recommend that you consult your Innovene technical representative for further advice on the use of LL6910KJ.

Properties	Test Method	Value	Units
Physical			
Melt flow rate			
Condition 4	ISO 1133	1.0	g/10 min
Conventional Density	ISO 1183 Method D	937	kg/m ³
Vicat softening temperature	ISO 306 Method A	121	°C
Slip (Erucamide)	INEOS method	800	ppm
Antiblock (Silica)	INEOS method	400	ppm
Additives: antioxidants			
Film*			
Dart drop impact	ASTM D1709 Method A	65	g
Tensile stress at yield	MD/TD ISO 1184	18/21	MPa
Tensile stress at break	MD/TD ISO 1184	54/36	MPa
Elongation at break	MD/TD ISO 1184	780/990	%

February, 2008

Published by
INEOS Polyolefins

LL6910KJ

1% Secant modulus	ISO 1184	450	MPa
Elmendorf tear strength MD/TD	ASTM D1922	35/325	g/25 μ m
Coefficient of friction	ASTM D1894	0.23	-
Haze	ASTM D1003	15	%
Gloss (45°)	ASTM D2457	50	% ₀₀

- Data should not be used for specification work

* 38 μ m film, 2:1 blow-up ratio, 230°C melt temperature - MD = machine direction TD = transverse direction

Extrusion

conditions

LL6910KJ in lean blends can be processed on most standard extrusion equipment. Optimisation of conditions may be necessary, depending on the exact blend used.

LL6910KJ rich film formulations are often processed on modified LDPE machinery, but for the best performance the use of purposely designed LLDPE machinery is recommended. Particular attention should be paid to maintaining a low melt temperature, and an efficient bubble cooling system should be employed. The recommended melt temperature range is 180 - 230°C.

Storage

LL6910KJ should be stored in a dry and dust free environment at temperatures below 50°C. Exposure to direct sunlight should be avoided, as this may lead to product deterioration.



LL6910KJ

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to psnohreg@innovene.com. Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical or pharmaceutical sector.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website www.ineospolyolefins.com. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

Exclusion of Liability

Although INEOS POLYOLEFINS endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS POLYOLEFINS is accurate and up to date, no representation or warranty, express or implied is made by INEOS POLYOLEFINS as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS POLYOLEFINS are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS POLYOLEFINS materials are suitable for the particular purpose intended and INEOS POLYOLEFINS shall not be responsible for any loss or damage caused by misuse of INEOS POLYOLEFINS products. To the maximum extent permitted by law, INEOS POLYOLEFINS accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS POLYOLEFINS materials or the use of INEOS POLYOLEFINS materials in conjunction with such other materials.