

Product Description

The HF1810P resin is a pelletized linear low density polyethylene selected by customers for applications that require maximum strength and toughness. This product offers excellent additive homogeneity, requires no transfer equipment modification, and facilitates clean and safe handling. Typical applications include heavy duty shipping sacks, trash can liners, commercial and industrial packaging, as well as food and consumer packaging. HF1810P offers enhanced film strength, drawdown, toughness and heat seal strength. In addition, this resin has excellent low temperature resistance for applications such as stretch film and frozen food packaging.

Regulatory Status

For regulatory compliance information, see HF1810P [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Asia-Pacific; Europe; North America; South & Central America
Application	Agriculture Film; Bags & Pouches; Can Liners; Film Wrap; Food Packaging Film; Heavy Duty Packaging; Lamination Film; Liner Film; Retail Carryout Bags; Shrink Film
Market	Flexible Packaging; Rigid Packaging
Processing Method	Blown Film; Sheet and Profile Extrusion

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	1.0	g/10 min	1.0	g/10 min	ASTM D1238
Base Resin Density, (23 °C)	0.918	g/cm ³	0.918	g/cm ³	ASTM D792
Product Density, (23 °C)	0.9225	g/cm ³	0.9225	g/cm ³	ASTM D792
Film					
Dart Drop Impact Strength, F50	200	g	200	g	ASTM D1709
Tensile Strength at Break					
MD	7540	psi	52	MPa	ASTM D882
TD	6530	psi	45	MPa	ASTM D882
Tensile Elongation at Break					
MD	710	%	710	%	ASTM D882
TD	750	%	750	%	ASTM D882
1% Secant Modulus					
MD	34800	psi	240	MPa	ASTM D882
TD	42000	psi	290	MPa	ASTM D882
Elmendorf Tear Strength					
MD	525	g	525	g	ASTM D1922
TD	720	g	720	g	ASTM D1922
Optical					
Haze	27	%	27	%	ASTM D2457
Gloss, (45°)	31	%	31	%	ASTM D1003
Additive					
Slip	1000	ppm	1000	ppm	LYB Method

Antiblock	6750 ppm	6750 ppm	LYB Method
Polymer Processing Aid	Present	Present	LYB Method

Notes

Film sample used for testing was 1.0 mil gauge, 2.5:1 BUR.

These are typical property values not to be construed as specification limits.

Processing Techniques

Recommended processing conditions for this product are a melt temperature of 400 - 450 °F and a 1.5 to 3.0:1 blow-up ratio.

Using proper techniques, these products can readily be drawn below 0.90 mils at optimum production rates.

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.